

FILAMENT TAPES

INFORMATIVE DATA SHEET



	†		\(\)	- JAK	
	backing thickness µm	total thickness µm	adhesion N/cm	breaking load N/cm	heavy weight packaging
NARFIL 500	28	120	> 8	> 220	•
NARGLASS 532	28	120	> 8	> 170	•
NARGLASS 539	28	130	> 8	> 220	•

It is good practice to use the product within 12 months from purchase date (6 months if jumbo roll). The rolls must be kept in their original packing. Keep the product out of the light and protect from direct heat sources. The tape must be kept in a dry place, at humidity level below 65%, preferably at a temperature between 15° C and 25° C. If the storage temperature is different, restore the tape back to above level before using it.

The values in the informative data sheets are the average results of tests made on our standard production and are not legally binding. The aesthetic and technical features may be subject to some changes caused by ageing, even though the quality level of the product is maintained. Nar shall not be liable for direct damages or for any consequence arising from the misuse of the product. We suggest the verification of the product suitability to the specific condition of use.



Additional indications are available in the last edition of the booklet "Recommendation regarding choice, storing and use of pressure sensitive tapes" published by Federazione Gomma Plastica.



FILAMENT TAPES

COMPOSITION

BACKING: biaxially oriented polypropylene film reinforced with longitudinal glass fibres
ADHESIVE: synthetic rubber / hydrocarbonic resins
CORE: recycled paper and paperboard

SUITABLE FOR

Heavy packaging; binding things; palletizing

AVAILABLE COLOURS

Transparent

The high performance hot melt adhesive and the glass fiber reinforced backing make this product the ideal choice for all packaging needs, also the heaviest.



ADHESION > 8 N/cm



BREAKING LOAD > 220 N/cm



HEAVY WEIGHT PACKAGING









FILAMENT TAPES

COMPOSITION

BACKING: biaxially oriented polypropylene film reinforced with cross weaved glass fibres
ADHESIVE: synthetic rubber / hydrocarbonic resins
CORE: recycled paper and paperboard

SUITABLE FOR

Heavy packaging; binding things; palletizing

AVAILABLE COLOURS

Transparent

The high performance hot melt adhesive and the glass fiber reinforced backing makes this product the ideal choice for all packaging needs, also the heaviest.



TOTAL THICKNESS 120 µm



BREAKING LOAD > 170 N/cm



HEAVY WEIGHT PACKAGING









FILAMENT TAPES

COMPOSITION

BACKING: biaxially oriented polypropylene film reinforced with cross weaved glass fibres
ADHESIVE: synthetic rubber / hydrocarbonic resins
CORE: recycled paper and paperboard

SUITABLE FOR

Heavy packaging; binding things; palletizing

AVAILABLE COLOURS

Transparent

The high performance hot melt adhesive and the glass fiber reinforced backing make this product the ideal choice for all packaging needs, also the heaviest.



TOTAL THICKNESS 130 µm



BREAKING LOAD > 220 N/cm



HEAVY WEIGHT PACKAGING





