












ACRILNAR TAPES

INFORMATIVE
DATA SHEET



	 backing thickness µm	 total thickness µm	 adhesion N/cm	 breaking load N/cm	 elongation at break %	 available colours	 heavy weight packaging	 medium weight packaging	 light weight packaging
ACRILNAR 220	25	39	> 2,0	> 36	> 116	● ○ ⊗			•
ACRILNAR 230	25	41	> 2,2	> 36	> 116	● ○ ⊗			•
ACRILNAR 230 LN	25	43	> 2,6	> 36	> 116	● ○ ⊗			•
ACRILNAR 240	28	44	> 2,2	> 39	> 116	● ○ ⊗			•
ACRILNAR 240 LN	28	46	> 2,6	> 39	> 116	● ○ ⊗			•
ACRILNAR 240 NN	28	49	> 2,9	> 39	> 116	● ○ ⊗			•
ACRILNAR 260	32	48	> 2,2	> 45	> 116	● ○ ⊗		•	
ACRILNAR 260 LN	32	50	> 2,6	> 45	> 116	● ○ ⊗		•	
ACRILNAR 260 NN	32	53	> 2,9	> 45	> 116	● ○ ⊗		•	
ACRILNAR 260 NN HT	32	55	> 3,1	> 45	> 116	● ○ ⊗		•	
ACRILNAR 265 NN	32	53	> 2,9	> 45	> 116	● ○ ⊗ ● ● ● ● ● ● ● ●		•	
ACRILNAR 265 HT	32	55	> 3,1	> 45	> 116	● ○ ⊗ ● ● ● ● ● ● ● ●		•	
ACRILNAR 270 NN	35	56	> 2,9	> 47	> 116	● ○ ⊗		•	
ACRILNAR 270 NN HT	35	58	> 3,1	> 47	> 116	● ○ ⊗		•	
ACRILNAR 276 NN	35	62	> 3,4	> 47	> 116	● ○ ⊗	•		
ACRILNAR 280 NN	40	65	> 3,1	> 54	> 116	● ○ ⊗	•		
ACRILNAR 290 NN	50	75	> 3,1	> 58	> 116	● ○ ⊗	•		

● brown ○ white ⊗ transparent ● red ● orange ● black ● yellow ● green ● light blue ● blue



NAR S.P.A.
Legnaro (PADOVA) ITALY
www.nar-spa.com

It is good practice to use the product within 12 months from purchase date (6 months if jumbo roll). The rolls must be kept in their original packing. Keep the product out of the light and protect from direct heat sources. The tape must be kept in a dry place, at humidity level below 65%, preferably at a temperature between 15° C and 25° C. If the storage temperature is different, restore the tape back to above level before using it. The values in the informative data sheets are the average results of tests made on our standard production and are not legally binding. The aesthetic and technical features may be subject to some changes caused by ageing, even though the quality level of the product is maintained. Nar shall not be liable for direct damages or for any consequence arising from the misuse of the product. We suggest the verification of the product suitability to the specific condition of use. Additional indications are available in the last edition of the booklet "Recommendation regarding choice, storing and use of pressure sensitive tapes" published by Federazione Gomma Plastica.







www.nar-spa.com/technical-notes.html



ACRILNAR 220

INFORMATIVE
DATA SHEET



-  FOOD CONTACT VERSION AVAILABLE
-  LIGHT WEIGHT PACKAGING
-  ORGANIC SOLVENTS FREE
-  SUITABLE FOR LOW TEMPERATURES PACKAGING

ACRILNAR

COMPOSITION

BACKING: biaxially oriented polypropylene film
ADHESIVE: water based acrylic polymers dispersion
CORE: recycled paper and paperboard

SUITABLE FOR

Hand dispensers and automatic sealing machines;
sealing of recycled cardboard boxes

AVAILABLE COLOURS

Brown - transparent

Excellent resistance at low temperature after application. The characteristics of the adhesive make it particularly resistant to ageing caused by light sources, while maintaining its functionality for a long time.

ACRILNAR products are also available in a food contact approved version: contact us for further information.



BACKING THICKNESS
25 μ m



ADHESION
> 2,0 N/cm



ELONGATION AT BREAK
> 116%



ACRILNAR 230

INFORMATIVE
DATA SHEET



LIGHT WEIGHT PACKAGING



ORGANIC SOLVENTS FREE



SUITABLE FOR LOW TEMPERATURES PACKAGING

ACRILNAR

COMPOSITION

BACKING: biaxially oriented polypropylene film
ADHESIVE: water based acrylic polymers dispersion
CORE: recycled paper and paperboard

SUITABLE FOR

Hand dispensers and automatic sealing machines;
sealing of recycled cardboard boxes

AVAILABLE COLOURS

Brown - white - transparent

Excellent resistance at low temperature after application. The characteristics of the adhesive make it particularly resistant to ageing caused by light sources, while maintaining its functionality for a long time.

ACRILNAR products are also available in a food contact approved version: contact us for further information.



BACKING THICKNESS
25 μ m



ADHESION
> 2,2 N/cm



ELONGATION AT BREAK
> 116%




MADE IN ITALY



ACRILNAR 230 LN

INFORMATIVE
DATA SHEET



-  LIGHT WEIGHT PACKAGING
-  ORGANIC SOLVENTS FREE
-  SUITABLE FOR LOW TEMPERATURES PACKAGING

ACRILNAR

COMPOSITION

BACKING: biaxially oriented polypropylene film
ADHESIVE: water based acrylic polymers dispersion
CORE: recycled paper and paperboard

SUITABLE FOR

Hand dispensers; sealing of recycled cardboard boxes

AVAILABLE COLOURS

Brown - white - transparent

Excellent resistance at low temperature after application. The characteristics of the adhesive make it particularly resistant to ageing caused by light sources, while maintaining its functionality for a long time.

ACRILNAR products are also available in a food contact approved version: contact us for further information.



BACKING THICKNESS
25 μ m



ADHESION
> 2,6 N/cm



LOW NOISE UNWINDING
(on request)



NAR S.P.A.
Legnaro (PADOVA)
ITALY
www.nar-spa.com

Membro di:





ACRILNAR 240

INFORMATIVE
DATA SHEET



LIGHT WEIGHT PACKAGING



ORGANIC SOLVENTS FREE



SUITABLE FOR LOW TEMPERATURES PACKAGING

ACRILNAR

COMPOSITION

BACKING: biaxially oriented polypropylene film
ADHESIVE: water based acrylic polymers dispersion
CORE: recycled paper and paperboard

SUITABLE FOR

Hand dispensers and automatic sealing machines;
sealing of recycled cardboard boxes

AVAILABLE COLOURS

Brown - white - transparent

Excellent resistance at low temperature after application. The characteristics of the adhesive make it particularly resistant to ageing caused by light sources, while maintaining its functionality for a long time.

ACRILNAR products are also available in a food contact approved version: contact us for further information.



BACKING THICKNESS
28 μ m



ADHESION
> 2,2 N/cm



BREAKING LOAD
> 39 N/cm



ACRILNAR 240 LN

INFORMATIVE
DATA SHEET



LIGHT WEIGHT PACKAGING



ORGANIC SOLVENTS FREE



SUITABLE FOR LOW TEMPERATURES PACKAGING

ACRILNAR

COMPOSITION

BACKING: biaxially oriented polypropylene film
ADHESIVE: water based acrylic polymers dispersion
CORE: recycled paper and paperboard

SUITABLE FOR

Hand dispensers and automatic sealing machines;
sealing of recycled cardboard boxes

AVAILABLE COLOURS

Brown - white - transparent

Excellent resistance at low temperature after application. The characteristics of the adhesive make it particularly resistant to ageing caused by light sources, while maintaining its functionality for a long time.

ACRILNAR products are also available in a food contact approved version: contact us for further information.



BACKING THICKNESS
28 μm



BREAKING LOAD
> 39 N/cm



LOW NOISE UNWINDING
(on request)



ACRILNAR 240 NN

INFORMATIVE
DATA SHEET



LIGHT WEIGHT PACKAGING



ORGANIC SOLVENTS FREE



SUITABLE FOR LOW TEMPERATURES PACKAGING

ACRILNAR

COMPOSITION

BACKING: biaxially oriented polypropylene film
ADHESIVE: water based acrylic polymers dispersion
CORE: recycled paper and paperboard

SUITABLE FOR

Hand dispensers; sealing of recycled cardboard boxes;
flexographic printing process

AVAILABLE COLOURS

Brown - white - transparent

Excellent resistance at low temperature after the application. High adhesive mass. The characteristics of the adhesive make it particularly resistant to ageing caused by light sources, while maintaining its functionality for a long time. Suitable for flexographic print. ACRILNAR products are also available in a food contact approved version: contact us for further information.



BACKING THICKNESS
28 μ m



SUITABLE FOR
FLEXOGRAPHIC PRINT



NOISELESS UNWINDING
(on request)



ACRILNAR 260

INFORMATIVE
DATA SHEET



MEDIUM WEIGHT PACKAGING



ORGANIC SOLVENTS FREE



SUITABLE FOR LOW TEMPERATURES PACKAGING

ACRILNAR

COMPOSITION

BACKING: biaxially oriented polypropylene film
ADHESIVE: water based acrylic polymers dispersion
CORE: recycled paper and paperboard

SUITABLE FOR

Hand dispensers and automatic sealing machines;
sealing of recycled cardboard boxes

AVAILABLE COLOURS

Brown - white - transparent

Excellent resistance at low temperature after application. The characteristics of the adhesive make it particularly resistant to ageing caused by light sources, while maintaining its functionality for a long time.

ACRILNAR products are also available in a food contact approved version: contact us for further information.



BACKING THICKNESS
32 μ m



ADHESION
> 2,2 N/cm



BREAKING LOAD
45 N/cm



ACRILNAR 260 LN

INFORMATIVE
DATA SHEET



MEDIUM WEIGHT PACKAGING



ORGANIC SOLVENTS FREE



SUITABLE FOR LOW TEMPERATURES PACKAGING

ACRILNAR

COMPOSITION

BACKING: biaxially oriented polypropylene film
ADHESIVE: water based acrylic polymers dispersion
CORE: recycled paper and paperboard

SUITABLE FOR

Hand dispensers; sealing of recycled cardboard boxes;
flexographic printing process

AVAILABLE COLOURS

Brown - white - transparent

Excellent resistance at low temperature after application. The characteristics of the adhesive make it particularly resistant to ageing caused by light sources, while maintaining its functionality for a long time.

ACRILNAR products are also available in a food contact approved version: contact us for further information.



BACKING THICKNESS
32 μ m



BREAKING LOAD
> 45 N/cm



LOW NOISE UNWINDING
(on request)



ACRILNAR 260 NN

INFORMATIVE
DATA SHEET



MEDIUM WEIGHT PACKAGING



ORGANIC SOLVENTS FREE



SUITABLE FOR LOW TEMPERATURES PACKAGING

ACRILNAR

COMPOSITION

BACKING: biaxially oriented polypropylene film
ADHESIVE: water based acrylic polymers dispersion
CORE: recycled paper and paperboard

SUITABLE FOR

Hand dispensers; sealing of recycled cardboard boxes;
flexographic printing process

AVAILABLE COLOURS

Brown - white - transparent

Excellent resistance at low temperature after the application. High adhesive mass. The characteristics of the adhesive make it particularly resistant to ageing caused by light sources, while maintaining its functionality for a long time. Suitable for flexographic print. ACRILNAR products are also available in a food contact approved version: contact us for further information.



BACKING THICKNESS
32 μ m



SUITABLE FOR
FLEXOGRAPHIC PRINT



NOISELESS UNWINDING
(on request)



ACRILNAR 260 NN HT

INFORMATIVE
DATA SHEET



HIGH ADHESIVE MASS



MEDIUM WEIGHT PACKAGING



ORGANIC SOLVENTS FREE



SUITABLE FOR LOW TEMPERATURES PACKAGING

ACRILNAR

COMPOSITION

BACKING: biaxially oriented polypropylene film
ADHESIVE: water based acrylic polymers dispersion
CORE: recycled paper and paperboard

SUITABLE FOR

Hand dispensers; sealing of recycled cardboard boxes;
flexographic printing process

AVAILABLE COLOURS

Brown - white - transparent

Excellent resistance at low temperature after the application. High adhesive mass. The characteristics of the adhesive make it particularly resistant to ageing caused by light sources, while maintaining its functionality for a long time. Suitable for flexographic print. ACRILNAR products are also available in a food contact approved version: contact us for further information.



BACKING THICKNESS
32 μm



ADHESION
> 3,1 N/cm



SUITABLE FOR
FLEXOGRAPHIC PRINT



ACRILNAR 265 NN

INFORMATIVE
DATA SHEET



MEDIUM WEIGHT PACKAGING



ORGANIC SOLVENTS FREE



SUITABLE FOR LOW TEMPERATURES PACKAGING

ACRILNAR

COMPOSITION

BACKING: pre-printed biaxially oriented polypropylene film

ADHESIVE: water based acrylic polymers dispersion

CORE: recycled paper and paperboard

SUITABLE FOR

Hand dispensers; sealing of recycled cardboard boxes;
flexographic printing process

AVAILABLE COLOURS

Red - orange - black - yellow - green - light blue - dark blue

Excellent resistance at low temperature after the application. High adhesive mass. The characteristics of the adhesive make it particularly resistant to ageing caused by light sources, while maintaining its functionality for a long time. Suitable for flexographic print. ACRILNAR products are also available in a food contact approved version: contact us for further information.



BACKING THICKNESS
32 μ m



SUITABLE FOR
FLEXOGRAPHIC PRINT



NOISELESS UNWINDING
(on request)



ACRILNAR 265 HT

INFORMATIVE
DATA SHEET



HIGH ADHESIVE MASS



MEDIUM WEIGHT PACKAGING



ORGANIC SOLVENTS FREE



SUITABLE FOR LOW TEMPERATURES PACKAGING

ACRILNAR

COMPOSITION

BACKING: pre-printed biaxially oriented polypropylene film

ADHESIVE: water based acrylic polymers dispersion

CORE: recycled paper and paperboard

SUITABLE FOR

Hand dispensers; sealing of recycled cardboard boxes;
flexographic printing process

AVAILABLE COLOURS

Red - orange - black - yellow - green - light blue - dark blue

Excellent resistance at low temperature after the application. High adhesive mass. The characteristics of the adhesive make it particularly resistant to ageing caused by light sources, while maintaining its functionality for a long time. Suitable for flexographic print. ACRILNAR products are also available in a food contact approved version: contact us for further information.



BACKING THICKNESS
32 μm



ADHESION
> 3,1 N/cm



SUITABLE FOR
FLEXOGRAPHIC PRINT



ACRILNAR 270 NN

INFORMATIVE
DATA SHEET



MEDIUM WEIGHT PACKAGING



ORGANIC SOLVENTS FREE



SUITABLE FOR LOW TEMPERATURES PACKAGING

ACRILNAR

COMPOSITION

BACKING: biaxially oriented polypropylene film
ADHESIVE: water based acrylic polymers dispersion
CORE: recycled paper and paperboard

SUITABLE FOR

Hand dispensers; sealing of recycled cardboard boxes;
flexographic printing process

AVAILABLE COLOURS

Brown - white - transparent

Excellent resistance at low temperature after the application. High adhesive mass. The characteristics of the adhesive make it particularly resistant to ageing caused by light sources, while maintaining its functionality for a long time. Suitable for flexographic print. ACRILNAR products are also available in a food contact approved version: contact us for further information.



BACKING THICKNESS
35 µm



SUITABLE FOR
FLEXOGRAPHIC PRINT



NOISELESS UNWINDING
(on request)



ACRILNAR 270 NN HT

INFORMATIVE
DATA SHEET



HIGH ADHESIVE MASS



MEDIUM WEIGHT PACKAGING



ORGANIC SOLVENTS FREE



SUITABLE FOR LOW TEMPERATURES PACKAGING

ACRILNAR

COMPOSITION

BACKING: biaxially oriented polypropylene film
ADHESIVE: water based acrylic polymers dispersion
CORE: recycled paper and paperboard

SUITABLE FOR

Hand dispensers; sealing of recycled cardboard boxes;
flexographic printing process

AVAILABLE COLOURS

Brown - white - transparent

Excellent resistance at low temperature after the application. High adhesive mass. The characteristics of the adhesive make it particularly resistant to ageing caused by light sources, while maintaining its functionality for a long time. Suitable for flexographic print. ACRILNAR products are also available in a food contact approved version: contact us for further information.



BACKING THICKNESS
35 μ m



SUITABLE FOR
FLEXOGRAPHIC PRINT



NOISELESS UNWINDING
(on request)



ACRILNAR 276 NN

INFORMATIVE
DATA SHEET



HIGH ADHESIVE MASS



HEAVY WEIGHT PACKAGING



ORGANIC SOLVENTS FREE



SUITABLE FOR LOW TEMPERATURES PACKAGING

ACRILNAR

COMPOSITION

BACKING: biaxially oriented polypropylene film
ADHESIVE: water based acrylic polymers dispersion
CORE: recycled paper and paperboard

SUITABLE FOR

Hand dispensers; sealing of recycled cardboard boxes;
flexographic printing process

AVAILABLE COLOURS

Brown - white - transparent

Excellent resistance at low temperature after the application. High adhesive mass. The characteristics of the adhesive make it particularly resistant to ageing caused by light sources, while maintaining its functionality for a long time. Suitable for flexographic print. ACRILNAR products are also available in a food contact approved version: contact us for further information.



BACKING THICKNESS
35 μ m



ADHESION
> 3,4 N/cm



BREAKING LOAD
> 47 N/cm



ACRILNAR 280 NN

INFORMATIVE
DATA SHEET



HIGH ADHESIVE MASS



HEAVY WEIGHT PACKAGING



ORGANIC SOLVENTS FREE



SUITABLE FOR LOW TEMPERATURES PACKAGING

ACRILNAR

COMPOSITION

BACKING: biaxially oriented polypropylene film
ADHESIVE: water based acrylic polymers dispersion
CORE: recycled paper and paperboard

SUITABLE FOR

Hand dispensers; sealing of recycled cardboard boxes;
flexographic printing process

AVAILABLE COLOURS

Brown - white - transparent

Excellent resistance at low temperature after the application. High adhesive mass. The characteristics of the adhesive make it particularly resistant to ageing caused by light sources, while maintaining its functionality for a long time. Suitable for flexographic print. ACRILNAR products are also available in a food contact approved version: contact us for further information.



BACKING THICKNESS
40 μ m



ADHESION
> 3,1 N/cm



BREAKING LOAD
> 54 N/cm



ACRILNAR 290 NN

INFORMATIVE
DATA SHEET



HIGH ADHESIVE MASS



HEAVY WEIGHT PACKAGING



ORGANIC SOLVENTS FREE



SUITABLE FOR LOW TEMPERATURES PACKAGING

ACRILNAR

COMPOSITION

BACKING: biaxially oriented polypropylene film
ADHESIVE: water based acrylic polymers dispersion
CORE: recycled paper and paperboard

SUITABLE FOR

Hand dispensers; sealing of recycled cardboard boxes;
flexographic printing process

AVAILABLE COLOURS

Brown - white - transparent

Excellent resistance at low temperature after the application. High adhesive mass. The characteristics of the adhesive make it particularly resistant to ageing caused by light sources, while maintaining its functionality for a long time. Suitable for flexographic print. ACRILNAR products are also available in a food contact approved version: contact us for further information.



BACKING THICKNESS
50 μ m



ADHESION
> 3,1 N/cm



BREAKING LOAD
> 58 N/cm