

PRINTED TAPES

COMPOSITION

BACKING: printed or pre-printed polyvinylchloride (PVC) film ADHESIVE: natural rubber / hydrocarbonic resins / solvent CORE: recycled paper and paperboard

SUITABLE FOR

Hand dispensers; sealing of recycled cardboard boxes; flexographic machine print

AVAILABLE COLOURS

Brown - white - transparent

The excellent mechanical characteristics of resistance, plasticity and adhesion, combined with silent unwinding, make this tape suitable for all packaging applications and traditional uses.



SPESSORE SUPPORTO 32 µm



PRINTED TAPE



SILENT UNWINDING



MEDIUM WEIGHT PACKAGING

HAND DISPENSER

WATER RESISTANT

NAR S.P.A. Legnaro (PADOVA) ITALY www.nar-spa.com









INFORMATIVE DATA SHEET



	-			jij.						*
	backing thickness μm	total thickness μm	adhesion N/cm	breaking load N/cm	elongation at break %	available colours	medium weight packaging	light weight packaging	automatic sealing machine	suitable for low temperatures packaging
POLIPRINT 240	28	47	> 2,0	> 39	> 116			•	•	•
POLINARPRINT 260	32	51	> 2,0	> 45	> 116		•		•	•
POLINARPRINT 265	32	51	> 2,0	> 45	> 116	••••	•		•	•
NARPRINT 140	32	51	> 1,5 (BI) > 1,8 (AV TR)	> 45	> 48	• 0 Ø	•			
NARPRINT 165	37	56	> 1,8	> 50	> 48		•			
NARPOUCH 240	28	47	n.r.	> 39	> 116	\otimes				
NARPOUCH 260	32	51	n.r.	> 45	> 116	\otimes				
RENEWA® TAPE 465	58	135	> 2,2	> 31	> 7	• •		•	•	

○ white

⊘ transparent

red

orange

😑 yellow

black

🔵 green

🔵 light blue 🛛 🌒 blue

🛑 fluo orange



NAR S.P.A. Legnaro (PADOVA) ITALY www.nar-spa.com It is good practice to use the product within 12 months from purchase date (6 months if jumbo roll). The rolls must be kept in their original packing. Keep the product out of the light and protect from direct heat sources. The tape must be kept in a dry place, at humidity level below 65%, preferably at a temperature between 15° C and 25° C. If the storage temperature is different, restore the tape back to above level before using it. The values in the informative data sheets are the average results of tests made on our standard production and are not legally binding. The aesthetic and technical features may be subject to some changes caused by ageing, even though the quality level of the product is maintained. Nar shall not be liable for direct damages or for any consequence arising from the misuse of the product. We suggest the verification of the product witability to the specific condition of use. Additional indications are available in the last edition of the booklet "Recommendation regarding choice, storing and use of pressure sensitive tapes" published by Federazione Gomma Plastica.



www.nar-spa.com/ technical-notes.html